

E-Polymers Tekaloy® G70A2 Impact Resistance, Easy Molding PC/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Impact Resistance, Easy Molding Information provided by E-Polymers Co. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_E-Polymers-Tekaloy-G70A2-Impact-Resistance-Easy-Molding-PCABS-Alloy.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 250 °C	7.0 g/10 min @Load 4.76 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	57.0 MPa	8270 psi	ASTM D638
Elongation at Break	>= 100 %	>= 100 %	ASTM D638
Flexural Yield Strength	84.0 MPa	12200 psi	ASTM D790
Flexural Modulus	2.20 GPa	319 ksi	ASTM D790
Izod Impact, Notched	6.00 J/cm	11.2 ft-lb/in	ASTM D256
	4.50 J/cm @Temperature -30.0 °C	8.43 ft-lb/in @Temperature -22.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	113 °C	235 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Processing Temperature	220 - 290 °C	428 - 554 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China