

ELASTO UK Dryflex® 660800S SEBS Based Material, Semi-Filled Qualities, 80A Hardness, Natural

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

The 660-series is recommended when the properties of the produced detail requires the advantages of the 500-series in combination with the 600-series. A semi-filled material can therefore combine the advantages of the other two series. The material has good flow and mechanical properties as well as reasonable scratch resistance. Information from Vita Thermoplastic Polymers (VTP). Vita Thermoplastic Polymers was acquired by HEXPOL and is now ELASTO

Order this product through the following link:

http://www.lookpolymers.com/polymer_ELASTO-UK-Dryflex-660800S-SEBS-Based-Material-Semi-Filled-Qualities-80A-Hardness-Natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Linear Mold Shrinkage	0.0080 - 0.020 cm/cm	0.0080 - 0.020 in/in	
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 190 °C	5.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80 @Thickness 4.00 mm	80 @Thickness 0.157 in	ASTM D2240
Tensile Strength at Break	9.00 MPa	1310 psi	ASTM D638
Elongation at Break	>= 600 %	>= 600 %	ASTM D638
100% Modulus	0.00400 GPa	0.580 ksi	ASTM D638
300% Modulus	0.00500 GPa	0.725 ksi	ASTM D638
Tear Strength	38.0 kN/m	217 pli	ASTM D624
Compression Set	28 %	28 %	at 23°C, 72 hrs; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Temperature Processing Properties	180 - 210 °C Metric	356 - 410 °F English	Comments
Descriptive Properties	Value	Comments	
Bonding to PP	Excellent		
Chemical Resistance	Good	Excluding organic solvents, aromatic and vegetable oils	
Color	Natural		
Weather Resistance	Excellent	Air ageing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China