

ELASTO UK Dryflex® 8006-101 Flame Retardant TPE for Extrusion, Natural, Halogen Free

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Vitaprene® thermoplastic elastomers combine the performance of most vulcanized rubber with the process properties of thermoplastics. Vitaprene® compounds permit sophisticated component design and thus will support a wide and flexible range of products. Flame retardant compounds will extend the application areas where resistance to ignition and burning are important features, while their performance characteristics in processing and finished component operation are of the same standard as the Vitaprene® general-purpose grades. The flame retardant compounds show an excellent resistance to a variety of polar fluids, such as water, aqueous systems and alcohols. However, in non-polar fluids, such as oil, resistance diminishes with increasing aromatic content. Weathering, including UV stability and ozone resistance is excellent. Processing: The flame retardant grades of Vitaprene® can easily be processed using conventional thermoplastic equipment for extrusion as well as other fabricating methods. The thermoplastic characteristics result in faster processing times and complete scrap recycling. The flame retardant compounds do not require pre-drying prior to processing. Information from Vita Thermoplastic Polymers (VTP). Vita Thermoplastic Polymers was acquired by HEXPOL and is now ELASTO

Order this product through the following link:

http://www.lookpolymers.com/polymer_ELASTO-UK-Dryflex-8006-101-Flame-Retardant-TPE-for-Extrusion-Natural-Halogen-Free.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ISO 2781
Melt Flow	9.0 g/10 min @Load 5.00 kg, Temperature 190 °C	9.0 g/10 min @Load 11.0 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	ISO 868
Tensile Strength at Break	5.20 MPa	754 psi	ISO 37
Elongation at Break	750 %	750 %	ISO 37
100% Modulus	0.00200 GPa	0.290 ksi	ISO 37
Tear Strength	23.0 kN/m	131 pli	Method C; ISO 34
Compression Set	40 %	40 %	Method B, at 23°C, 24 hrs; ISO 815

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Basic Descriptive Properties	Halogen Free Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China