

## EMS-Griltech Griltech® 9E Copolyester Hotmelt Adhesive (Technical Applications)

Category : Polymer , Adhesive , Thermoplastic , Polyester , TP

### Material Notes:

Description: GRILTEX adhesive products, either in pellet or powdered form, are used to coat apparel interlining substrates. Interlining substrates, coated with GRILTEX adhesive products, provides for excellent resistance and dimensional stability of the finished garment. For technical applications, GRILTEX adhesive products are used to optimize the manufacturing process for the production of automotive interior components or parts for other applications. All values were determined on dried pellets. Applications: Automotive Interiors (Door Panel, Headliner, Seat), Filters, Adhesive Films (supported), Home Furnishing Bonding Properties: Metal, Paper, Wood, PVC, PUR (Foam), Polyester Data provided by EMS-Griltech.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_EMS-Griltech-Griltech-9E-Copolyester-Hotmelt-Adhesive-Technical-Applications.php](http://www.lookpolymers.com/polymer_EMS-Griltech-Griltech-9E-Copolyester-Hotmelt-Adhesive-Technical-Applications.php)

Physical Properties	Metric	English	Comments
Viscosity	350000 cP	350000 cP	2.16 kg load; ISO 1133
	@Temperature 160 °C	@Temperature 320 °F	
Melt Flow	30 g/10 min	30 g/10 min	cm <sup>3</sup> /10 min; ISO 1133
	@Load 2.16 kg, Temperature 160 °C	@Load 4.76 lb, Temperature 320 °F	

Thermal Properties	Metric	English	Comments
Melting Point	118 - 123 °C	244 - 253 °F	DSC

Processing Properties	Metric	English	Comments
Processing Temperature	120 - 150 °C	248 - 302 °F	Lamination Adhesive
	140 - 170 °C	284 - 338 °F	Films Die Head
Die Temperature	170 - 210 °C	338 - 410 °F	Hotmelt Coating Slot Die
Roll Temperature	160 - 200 °C	320 - 392 °F	Hotmelt Coating Multi Roller
	180 - 220 °C	356 - 428 °F	Engraved Roller

Descriptive Properties	Value	Comments
Crystallization Speed	Slow	
Form of Delivery	Granules, Powder	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China