

EMS-Griltech Griltech® D 1533E Copolyester Hotmelt Adhesive (Technical Applications)

Category : Polymer , Adhesive , Thermoplastic , Polyester, TP

Material Notes:

Description: GRILTEX adhesive products, either in pellet or powdered form, are used to coat apparel interlining substrates. Interlining substrates, coated with GRILTEX adhesive products, provides for excellent resistance and dimensional stability of the finished garment. For technical applications, GRILTEX adhesive products are used to optimize the manufacturing process for the production of automotive interior components or parts for other applications. All values were determined on dried pellets. Applications: Automotive Interiors (Door Panel, Seat), Filters, Home Furnishing, Flexible Coatings Bonding Properties: Metal, Paper, Wood, PVC, PUR (Foam/Film), Polyester Data provided by EMS-Griltech.

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Griltech-Griltech-D-1533E-Copolyester-Hotmelt-Adhesive-Technical-Applications.php

Physical Properties	Metric	English	Comments
Viscosity	30000 cP @Temperature 190 °C	30000 cP @Temperature 374 °F	2.16 kg load; ISO 1133
Melt Flow	350 g/10 min @Load 2.16 kg, Temperature 190 °C	350 g/10 min @Load 4.76 lb, Temperature 374 °F	cm ³ /10 min; ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	140 - 150 °C	284 - 302 °F	DSC

Processing Properties	Metric	English	Comments
Processing Temperature	150 - 160 °C	302 - 320 °F	Lamination Adhesive
Die Temperature	160 - 180 °C	320 - 356 °F	Hotmelt Coating Slot Die
Roll Temperature	160 - 180 °C	320 - 356 °F	Hotmelt Coating Multi Roller
	180 - 220 °C	356 - 428 °F	Engraved Roller

Descriptive Properties	Value	Comments
Crystallization Speed	Fast	
Form of Delivery	Granules	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China