

EMS-Grivory Grivory® HTV-3H1 black 9205 PA6T/6I-GF30

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Product description: Grivory HTV-3H1 black 9205 is a 30% glass fiber reinforced engineering thermoplastic material based on a semi-crystalline, partially aromatic copolyamide. Acc. to ISO: PA 6T/6I. Acc. to ASTM: PPA, polyphthalamide The main distinguishing feature of Grivory HT, when compared to other polyamides, is its good performance at high temperatures providing parts which are stiffer, stronger and have better heat distortion stability and chemical resistance. Grivory HT is suitable for production of technical parts in the application fields of:ElectroElectronicsAutomotiveMechanical engineeringDomestic applianceInformation provided by EMS Grivory

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-HTV-3H1-black-9205-PA6T6I-GF30.php

Physical Properties	Metric	English	Comments
Density	1.44 g/cc	0.0520 lb/in ³	ISO 1183
Water Absorption	3.5 %	3.5 %	ISO 62
Moisture Absorption	1.80 %	1.80 %	ISO 62
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	270 MPa	39200 psi	conditioned; ISO 2039-1
	280 MPa	40600 psi	dry; ISO 2039-1
Tensile Strength at Break	170 MPa	24700 psi	conditioned; ISO 527-1/-2
	190 MPa	27600 psi	dry; ISO 527-1/-2
Elongation at Break	2.0 %	2.0 %	dry; ISO 527-1/-2
	2.0 %	2.0 %	conditioned; ISO 527-1/-2
Tensile Modulus	11.0 GPa	1600 ksi	conditioned; ISO 527-1/-2
	11.0 GPa	1600 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	dry; ISO 179/1eU
	5.00 J/cm ²	23.8 ft-lb/in ²	conditioned; ISO 179/1eU
	5.00 J/cm ²	23.8 ft-lb/in ²	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	5.00 J/cm ²	23.8 ft-lb/in ²	

Mechanical Properties	Metric @ Temperature 30.0 °C	English @ Temperature 86.0 °F	conditioned; ISO 179/1eU Comments
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	dry; ISO 179/1eA
	0.700 J/cm ²	3.33 ft-lb/in ²	conditioned; ISO 179/1eA
	0.700 J/cm ² @Temperature 30.0 °C	3.33 ft-lb/in ² @Temperature 86.0 °F	dry; ISO 179/1eU
	0.700 J/cm ² @Temperature 30.0 °C	3.33 ft-lb/in ² @Temperature 86.0 °F	conditioned; ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	50.0 µm/m-°C	27.8 µin/in-°F	ISO 11359-1/-2
Melting Point	325 °C	617 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	150 °C	302 °F	long term; EMS
	250 °C	482 °F	short term; EMS
Deflection Temperature at 1.8 MPa (264 psi)	280 °C	536 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	155 °C	311 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	dry; IEC 60093
	1.00e+13 ohm-cm	1.00e+13 ohm-cm	conditioned; IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Strength	30.0 kV/mm	762 kV/in	dry; IEC 60243-1
	30.0 kV/mm	762 kV/in	conditioned; IEC 60243-1
Comparative Tracking Index	575 V	575 V	conditioned; IEC 60112

Descriptive Properties	Value	Comments
Automotive	Exterior	
	Fuel systems	
	Interior	

Descriptive Properties	Value	Comments
	Powertrain and Chassis	
Form	Granules	
Industry & Consumer goods	Housewares	
	Hydraulics & Pneumatics	
	Mechanical Engineering	
	Power transmission	
	Sports & Leisure	
	Tools & Accessories	
Processing	Injection Molding	
Special Characteristics	Improved heat resistance	
	Improved UV resistance (outdoor use)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China