

## EMS-Grivory Grivory® L 16 W 20 black 9995 PA12

Category : Polymer , Thermoplastic , Nylon , Nylon 12

### Material Notes:

**Product Description:** Grilamid L 16 W 20 is a semi-flexible low viscosity, heat stabilized PA12 injection molding grade. The main characteristics of this product are: Easy flowing?High impact strength even at low temperatures?Good UV-stability?High elongation at yield  
**Application examples:** Grilamid L16 W 20 has been developed for applications having long flow paths and requiring flexibility. Typical applications are electrical cable binders used in aircraft and ship construction as well as Off-shore installations  
 Information provided by EMS Grivory

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_EMS-Grivory-Grivory-L-16-W-20-black-9995-PA12.php](http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-L-16-W-20-black-9995-PA12.php)

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.5 %	1.5 %	ISO 62
Moisture Absorption	0.700 %	0.700 %	ISO 62
Linear Mold Shrinkage, Flow	0.0080 cm/cm	0.0080 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	conditioned, 15s; ISO 868
Tensile Strength at Break	40.0 MPa	5800 psi	conditioned; ISO 527-1/-2
	50.0 MPa	7250 psi	dry; ISO 527-1/-2
Tensile Strength, Yield	30.0 MPa	4350 psi	dry; ISO 527-1/-2
	35.0 MPa	5080 psi	dry; ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	conditioned; ISO 527-1/-2
	<= 50 %	<= 50 %	dry; ISO 527-1/-2
Elongation at Yield	20 %	20 %	conditioned; ISO 527-1/-2
	25 %	25 %	dry; ISO 527-1/-2
Tensile Modulus	0.500 GPa	72.5 ksi	conditioned; ISO 527-1/-2
	0.520 GPa	75.4 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	dry; ISO 179/1eU

Mechanical Properties	NB Metric	NB English	conditioned; ISO 179/1eU Comments
	NB	NB	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	NB	NB	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Charpy Impact, Notched	4.00 J/cm <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	conditioned; ISO 179/1eA
	0.300 J/cm <sup>2</sup>	1.43 ft-lb/in <sup>2</sup>	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	140 µm/m-°C	77.8 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	160 µm/m-°C	88.9 µin/in-°F	ISO 11359-1/-2
Melting Point	174 °C	345 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	80.0 - 110 °C	176 - 230 °F	long term; EMS
	150 °C	302 °F	short term; EMS
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	45.0 °C	113 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	conditioned; IEC 60093
Surface Resistance	1.00e+11 ohm	1.00e+11 ohm	IEC 60093
Dielectric Strength	32.0 kV/mm	813 kV/in	conditioned; IEC 60243-1
Comparative Tracking Index	600 V	600 V	conditioned; IEC 60112

Descriptive Properties	Value	Comments
Additives	Plasticizer	
Automotive	Automotive electr. and electronics, lighting	
	Powertrain and Chassis	
Electricals & Electronics	Connectors	

Descriptive Properties	Value distribution	Comments
Form	Granules	
Industry & Consumer goods	Hydraulics & Pneumatics	
	Mechanical Engineering	
	Tools & Accessories	
Processing	Injection Molding	
Product Attributes	Flexible	
	Improved flowability and demoulding	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China