

## EMS-Grivory Grivory® LC-3H black PA12-CF30

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, Carbon Fiber Filled

### Material Notes:

Product description: Grilamid LC-3H BLACK is a Polyamide 12 injection molding product reinforced with 30 % carbon fibers. The product is inherently black and is only available in this color. Main Attributes: high stiffness at low weight very low moisture absorption electrically conductive favorable abrasion and wear properties low coefficient of thermal expansion low mould shrinkage easy processing good chemical and UV resistance Grilamid LC-15H BLACK is particularly suitable for technical components in the following application fields: Sport and leisure goods Lightweight designs and prototypes Tools and instruments Conductive electrical devices Explosion proof safety devices Information provided by EMS Grivory

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_EMS-Grivory-Grivory-LC-3H-black-PA12-CF30.php](http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-LC-3H-black-PA12-CF30.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.1 %	1.1 %	ISO 62
Moisture Absorption	0.600 %	0.600 %	ISO 62
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0030 cm/cm	0.0030 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	130 MPa	18900 psi	conditioned; ISO 2039-1
Tensile Strength at Break	140 MPa	20300 psi	conditioned; ISO 527-1/-2
	150 MPa	21800 psi	dry; ISO 527-1/-2
Elongation at Break	3.5 %	3.5 %	dry; ISO 527-1/-2
	4.0 %	4.0 %	conditioned; ISO 527-1/-2
Tensile Modulus	13.0 GPa	1890 ksi	conditioned; ISO 527-1/-2
	15.0 GPa	2180 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	6.00 J/cm <sup>2</sup>	28.6 ft-lb/in <sup>2</sup>	conditioned; ISO 179/1eU
	6.00 J/cm <sup>2</sup>	28.6 ft-lb/in <sup>2</sup>	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Charpy Impact, Notched	1.30 J/cm <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	conditioned; ISO 179/1eA
	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	conditioned; ISO 179/1eU

Mechanical Properties	Metric @ Temperature 30.0 °C	English @ Temperature 86.0 °F	Comments
-----------------------	---------------------------------	----------------------------------	----------

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	10.0 µm/m-°C	5.56 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	130 µm/m-°C	72.2 µin/in-°F	ISO 11359-1/-2
Melting Point	178 °C	352 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	90.0 - 120 °C	194 - 248 °F	long term; EMS
	150 °C	302 °F	short term; EMS
Deflection Temperature at 1.8 MPa (264 psi)	165 °C	329 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	125 °C	257 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	10000 ohm-cm	10000 ohm-cm	conditioned; IEC 60093
Surface Resistance	50 ohm	50 ohm	IEC 60093

Descriptive Properties	Value	Comments
Electricals & Electronics	Mobile phones and other portable devices	
Form	Granules	
Industry & Consumer goods	Mechanical Engineering	
	Medical devices	
	Power transmission	
	Sports & Leisure	
	Tools & Accessories	
Processing	Injection Molding	
Special Characteristics	Anti-static	
	High impact or impact modified	
	Improved UV resistance (outdoor use)	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**