

EMS-Grivory Grivory® LVX-65H SST black 9288 PA12-GF65

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, 50% Glass Fiber Filled

Material Notes:

Product description: Grilamid LVX-65H SST black 9288 is a 65% glass fiber reinforced, heat stabilized engineering thermoplastic based on polyamide 12 for complex structural parts with the following product profile: Very high stiffness and strengthExcellent impact and notched impact strengthExcellent UV, heat and chemical resistanceVery low moisture absorptionSuitable for often repeated steam sterilizationGood flow characteristicsHigh molding precision, low warpage Grilamid LVX-65H SST black 9288 is suitable for production of technical parts in applications such as: Housings of electronic devicesAutomotiveMechanical engineeringSafety componentsHousings of medical devices and instrumentsInformation provided by EMS Grivory

Order this product through the following link:

http://www.lookpolymers.com/polymer_EMS-Grivory-Grivory-LVX-65H-SST-black-9288-PA12-GF65.php

Physical Properties	Metric	English	Comments
Density	1.70 g/cc	0.0614 lb/in ³	ISO 1183
Water Absorption	0.80 %	0.80 %	ISO 62
Moisture Absorption	0.400 %	0.400 %	ISO 62
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0030 cm/cm	0.0030 in/in	ISO 294-4, 2577

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	190 MPa	27600 psi	conditioned; ISO 2039-1
	210 MPa	30500 psi	dry; ISO 2039-1
Tensile Strength at Break	185 MPa	26800 psi	conditioned; ISO 527-1/-2
	200 MPa	29000 psi	dry; ISO 527-1/-2
Elongation at Break	2.5 %	2.5 %	dry; ISO 527-1/-2
	2.5 %	2.5 %	conditioned; ISO 527-1/-2
Tensile Modulus	17.0 GPa	2470 ksi	conditioned; ISO 527-1/-2
	19.0 GPa	2760 ksi	dry; ISO 527-1/-2
Charpy Impact Unnotched	8.50 J/cm ²	40.4 ft-lb/in ²	dry; ISO 179/1eU
	8.50 J/cm ²	40.4 ft-lb/in ²	conditioned; ISO 179/1eU
	8.00 J/cm ² @Temperature 30.0 °C	38.1 ft-lb/in ² @Temperature 86.0 °F	dry; ISO 179/1eU

Mechanical Properties	Metric ¹ /cm ²	English ¹ lb/in ²	Comments
	@Temperature 30.0 °C	@Temperature 86.0 °F	conditioned; ISO 179/1eU
Charpy Impact, Notched	2.00 J/cm ²	9.52 ft-lb/in ²	dry; ISO 179/1eA
	2.00 J/cm ²	9.52 ft-lb/in ²	conditioned; ISO 179/1eA
	2.00 J/cm ²	9.52 ft-lb/in ²	dry; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	
	2.00 J/cm ²	9.52 ft-lb/in ²	conditioned; ISO 179/1eU
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	10.0 μm/m-°C	5.56 μin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	70.0 μm/m-°C	38.9 μin/in-°F	ISO 11359-1/-2
Melting Point	178 °C	352 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	90.0 - 120 °C	194 - 248 °F	long term; EMS
	150 °C	302 °F	short term; EMS
Deflection Temperature at 1.8 MPa (264 psi)	175 °C	347 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	160 °C	320 °F	ISO 75-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	conditioned; IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Strength	35.0 kV/mm	889 kV/in	dry; IEC 60243-1
	35.0 kV/mm	889 kV/in	conditioned; IEC 60243-1
Comparative Tracking Index	600 V	600 V	conditioned; IEC 60112

Descriptive Properties	Value	Comments
Automotive	Automotive electr. and electronics, lighting	
	Compressed air systems	
	Hydraulic systems	
	Powertrain and Chassis	

Descriptive Properties	Value ctors	Comments
	Electrical appliances	
	Electrical equipment	
	Mobile phones and other portable devices	
Form	Granules	
Industry & Consumer goods	Housewares	
	Hydraulics & Pneumatics	
	Mechanical Engineering	
	Medical devices	
	Power transmission	
	Sanitary, water and gas supply	
	Sports & Leisure	
	Tools & Accessories	
Processing	Injection Molding	
Product Attributes	Improved flowability and demoulding	
Special Characteristics	High impact or impact modified	
	Improved heat resistance	
	Improved UV resistance (outdoor use)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China