

EPICHEM PA 6/66 GF 30 Polyamide 6/66, 30% Glass

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6 , 30% Glass Fiber Reinforced

Material Notes:

Characteristics: 30% glass fibre filled

Order this product through the following link:

http://www.lookpolymers.com/polymer_EPICHEM-PA-666-GF-30-Polyamide-666-30-Glass.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ASTM D792, ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	135 MPa	19600 psi	ASTM D638, ISO R527
Flexural Strength	200 MPa	29000 psi	ASTM D790, ISO 178
Izod Impact, Notched	0.550 J/cm @Thickness 3.20 mm, Temperature 23.0 °C	1.03 ft-lb/in @Thickness 0.126 in, Temperature 73.4 °F	ASTM D256, ISO 180/4a

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	165 °C	329 °F	ASTM D648, ISO 75

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China