

Eagle Brass 1008 Low Carbon Steel, 1/4 Hardened

Category: Metal, Ferrous Metal, Carbon Steel, Low Carbon Steel

Material Notes:

1008 is a standard grade Carbon Steel. This alloy is generally used for "commercial quality" cold rolled steel. It is an economical, general purpose steel grade offering moderate strength and toughness. As a standard grade, 1008 steel is used in many common, low-stress applications. Weldability and brazeability are excellent. Typical uses include infrared counter measure flare substrate, electronic parts carrier, low ohm etched heating element and conductor grid elements. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-1008-Low-Carbon-Steel-14-Hardened.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|--------------|-------------|
| Density | 7.86 g/cc | 0.284 lb/in³ | As Annealed |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|---------------|-------------------|-------------|
| Tensile Strength | 310 - 448 MPa | 45000 - 65000 psi | |
| Elongation at Break | 13 - 27 % | 13 - 27 % | in 2 inches |
| Tensile Modulus | 200 GPa | 29000 ksi | |

| Thermal Properties | Metric | English | Comments |
|----------------------|-------------------------------|-----------------------------------|----------|
| CTE, linear | 15.8 μm/m-°C | 8.80 µin/in-°F | |
| | @Temperature 20.0 - 649 °C | @Temperature 68.0 - 1200 °F | |
| Thermal Conductivity | 36.0 W/m-K | 250 BTU-in/hr-ft ² -°F | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|-------------|-------------|-----------------------|
| Carbon, C | <= 0.10 % | <= 0.10 % | |
| Iron, Fe | >= 99.685 % | >= 99.685 % | Calculated as Balance |
| Manganese, Mn | <= 0.15 % | <= 0.15 % | |
| Phosphorous, P | <= 0.030 % | <= 0.030 % | |
| Sulfur, S | <= 0.035 % | <= 0.035 % | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China