

## Eagle Brass 101 OFE COPPER (Certified), 1/4 Hard

Category : Metal , Nonferrous Metal , Copper Alloy

**Material Notes:**

Alloy 101 is known as Oxygen-Free Electronic (OFE). It reaches a minimum of 101% IACS conductivity rating. It is the most expensive out of the 101- 110 group because of its higher purity. Information provided by Eagle Brass Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eagle-Brass-101-OFE-COPPER-Certified-14-Hard.php](http://www.lookpolymers.com/polymer_Eagle-Brass-101-OFE-COPPER-Certified-14-Hard.php)

Physical Properties	Metric	English	Comments
Density	8.94 g/cc	0.323 lb/in <sup>3</sup>	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	18 - 51	18 - 51	Thickness > 0.020 Inch
Tensile Strength, Ultimate	234 - 290 MPa	34000 - 42000 psi	
Tensile Strength, Yield	179 - 269 MPa	26000 - 39000 psi	0.2% offset
Elongation at Break	13 - 33 %	13 - 33 %	in 2 in.
Tensile Modulus	117 GPa	17000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	17.6 $\mu\text{m}/\text{m}\cdot\text{°C}$	9.80 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	390.8 W/m-K	2712 BTU-in/hr-ft <sup>2</sup> -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	>= 99.99 %	>= 99.99 %	
Oxygen, O	<= 0.00050 %	<= 0.00050 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000176 ohm-cm	0.00000176 ohm-cm	Annealed

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China