

## Eagle Brass 102 OF COPPER (Non-Certified), Spring

Category : Metal , Nonferrous Metal , Copper Alloy

### Material Notes:

Alloy 102 is an oxygen-free copper which has better forming, resistance to hydrogen embrittlement, and brazing characteristics than C110 ETP. C102 has good solder-ability and corrosion resistance and is used for high current applications. Information provided by Eagle Brass Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eagle-Brass-102-OF-COPPER-Non-Certified-Spring.php](http://www.lookpolymers.com/polymer_Eagle-Brass-102-OF-COPPER-Non-Certified-Spring.php)

Physical Properties	Metric	English	Comments
Density	8.94 g/cc	0.323 lb/in <sup>3</sup>	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	60 - 66	60 - 66	Thickness > 0.020 Inch
Tensile Strength, Ultimate	345 - 400 MPa	50000 - 58000 psi	
Tensile Strength, Yield	331 - 393 MPa	48000 - 57000 psi	0.2% offset
Elongation at Break	2.0 - 4.0 %	2.0 - 4.0 %	in 2 in.
Tensile Modulus	117 GPa	17000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	17.6 µm/m-°C	9.80 µin/in-°F	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	390.8 W/m-K	2712 BTU-in/hr-ft <sup>2</sup> -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	>= 99.9 %	>= 99.9 %	
Oxygen, O	<= 0.0010 %	<= 0.0010 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000176 ohm-cm	0.00000176 ohm-cm	Annealed

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China