

Eagle Brass 18665 MSP1, 1/4 Hard

Category : Metal , Nonferrous Metal , Copper Alloy

Material Notes:

MSP-1 high performance copper alloy with magnesium has high conductivity (63% IACS), high strength and excellent thermal creep properties. Typical uses include terminals, connectors, relays, springs, switches, sockets, and junction boxes. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-18665-MSP1-14-Hard.php

Physical Properties	Metric	English	Comments
Density	8.94 g/cc	0.323 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	359 - 448 MPa	52000 - 65000 psi	
Tensile Strength, Yield	296 - 407 MPa	43000 - 59000 psi	0.2% offset
Elongation at Break	>= 15 %	>= 15 %	in 2 in.
Tensile Modulus	117 GPa	17000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	17.3 $\mu\text{m}/\text{m}\cdot\text{°C}$	9.60 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	456.5 W/m-K	3168 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	99 %	99 %	
Magnesium, Mg	0.70 %	0.70 %	
Phosphorous, P	0.040 %	0.040 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000283 ohm-cm	0.00000283 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China