

Eagle Brass 210 Gilding Metal, Extra Spring

Category : Metal , Nonferrous Metal , Copper Alloy , Brass

Material Notes:

CDA 210 is known for its resistance to corrosion. The alloy also lends itself to deep drawing such as bullet jackets and electrical applications where formability and conductivity are required. Typical uses are for architectural ornamental trim, emblems, plaques, connectors, rotor bars, AC motors, fasteners, bullet jackets, fuse caps, firing pins, and coins. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-210-Gilding-Metal-Extra-Spring.php

Physical Properties	Metric	English	Comments
Density	8.86 g/cc	0.320 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	65 - 69	65 - 69	Thickness > 0.020 Inch
Tensile Strength, Ultimate	421 - 476 MPa	61000 - 69000 psi	
Tensile Strength, Yield	414 - 469 MPa	60000 - 68000 psi	0.2% offset
Elongation at Break	>= 2.0 %	>= 2.0 %	in 2 in.
Tensile Modulus	117 GPa	17000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m}/\text{m}\cdot\text{C}$	10.0 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	233 W/m-K	1620 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	95 %	95 %	
Zinc, Zn	5.0 %	5.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000318 ohm-cm	0.00000318 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China