

## Eagle Brass 220 Commercial Bronze, Spring

Category : Metal , Nonferrous Metal , Copper Alloy , Brass

**Material Notes:**

CDA 220 is known for having very good corrosion resistance, great cold workability and good hot workability for drawing, blanking, coining, stamping, piercing and punching. Typical uses include plumbing brass, small arms cartridges, cable wrap, marine hardware, flexible tube, blots, screws, wave guides costume jewelry and kick plates. Information provided by Eagle Brass Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eagle-Brass-220-Commercial-Bronze-Spring.php](http://www.lookpolymers.com/polymer_Eagle-Brass-220-Commercial-Bronze-Spring.php)

Physical Properties	Metric	English	Comments
Density	8.80 g/cc	0.318 lb/in <sup>3</sup>	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	70 - 72	70 - 72	Thickness > 0.020 Inch
Tensile Strength, Ultimate	476 - 531 MPa	69000 - 77000 psi	
Tensile Strength, Yield	448 - 490 MPa	65000 - 71000 psi	0.2% offset
Elongation at Break	1.0 - 2.0 %	1.0 - 2.0 %	in 2 in.
Tensile Modulus	117 GPa	17000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.4 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	10.2 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 20.0 - 300 $^{\circ}\text{C}$	@Temperature 68.0 - 572 $^{\circ}\text{F}$	
Thermal Conductivity	188.5 W/m-K	1308 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Copper, Cu	90 %	90 %	
Zinc, Zn	10 %	10 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000405 ohm-cm	0.00000405 ohm-cm	Annealed

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China