

## Eagle Brass 230 Red Brass, 1/2 Hard

Category : Metal , Nonferrous Metal , Copper Alloy , Brass

**Material Notes:**

CDA 230 is known for having an electrical conductivity of 37% IACS, red color, corrosion resistance, excellent formability and moderate strength. Typical uses include costume jewelry, eyelets, fasteners, conduit, heat exchangers, flexible metal hose, pipe, and couplings. Information provided by Eagle Brass Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eagle-Brass-230-Red-Brass-12-Hard.php](http://www.lookpolymers.com/polymer_Eagle-Brass-230-Red-Brass-12-Hard.php)

Physical Properties	Metric	English	Comments
Density	8.75 g/cc	0.316 lb/in <sup>3</sup>	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	56 - 64	56 - 64	Thickness > 0.020 Inch
Tensile Strength, Ultimate	352 - 421 MPa	51000 - 61000 psi	
Tensile Strength, Yield	296 - 372 MPa	43000 - 54000 psi	0.2% offset
Elongation at Break	8.0 - 21 %	8.0 - 21 %	in 2 in.
Tensile Modulus	117 GPa	17000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.7 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.4 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	159.1 W/m-K	1104 BTU-in/hr-ft <sup>2</sup> -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	85 %	85 %	
Zinc, Zn	15 %	15 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000481 ohm-cm	0.00000481 ohm-cm	Annealed

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China