

## Eagle Brass 240 Low Brass, 1/2 Hard

Category : Metal , Nonferrous Metal , Copper Alloy , Brass

**Material Notes:**

CDA 240 has excellent ductility, corrosion resistance and strength which allows it to be deep drawn, etched, stamped, blanked and bent.

Typical uses include musical instruments, battery caps, flexible hose, and decorative pieces because of its yellow color. Information provided by Eagle Brass Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eagle-Brass-240-Low-Brass-12-Hard.php](http://www.lookpolymers.com/polymer_Eagle-Brass-240-Low-Brass-12-Hard.php)

Physical Properties	Metric	English	Comments
Density	8.66 g/cc	0.313 lb/in <sup>3</sup>	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	56 - 64	56 - 64	Thickness > 0.020 Inch
Tensile Strength, Ultimate	379 - 448 MPa	55000 - 65000 psi	
Tensile Strength, Yield	241 - 345 MPa	35000 - 50000 psi	0.2% offset
Elongation at Break	12 - 25 %	12 - 25 %	in 2 in.
Tensile Modulus	110 GPa	16000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	19.1 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	10.6 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 20.0 - 300 $^{\circ}\text{C}$	@Temperature 68.0 - 572 $^{\circ}\text{F}$	
Thermal Conductivity	140 W/m-K	972 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Copper, Cu	80 %	80 %	
Zinc, Zn	20 %	20 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000556 ohm-cm	0.00000556 ohm-cm	Annealed

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China