

Eagle Brass 260 Cartridge Brass, 3/4 Hard

Category : Metal , Nonferrous Metal , Copper Alloy , Brass

Material Notes:

Alloy C260 is commonly used for electrical components, electronic parts, and mechanical fasteners. The alloy has good strength but poor stress relaxation characteristics and does not make a particularly good spring material. The solderability of the alloy is severely impaired by its high zinc content. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-260-Cartridge-Brass-34-Hard.php

Physical Properties	Metric	English	Comments
Density	8.53 g/cc	0.308 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	65 - 70	65 - 70	Thickness > 0.020 Inch
Tensile Strength, Ultimate	441 - 510 MPa	64000 - 74000 psi	
Tensile Strength, Yield	379 - 476 MPa	55000 - 69000 psi	0.2% offset
Elongation at Break	8.0 - 25 %	8.0 - 25 %	in 2 in.
Tensile Modulus	110 GPa	16000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	20.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	11.1 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	121 W/m-K	840 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	70 %	70 %	
Zinc, Zn	30 %	30 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000636 ohm-cm	0.00000636 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China