

Eagle Brass 430 Ferritic Stainless Steel, Full Hardened

Category : Metal , Ferrous Metal , Stainless Steel , T 400 Series Stainless Steel

Material Notes:

Type 430 is one of the most widely used of the "non-hardenable" ferritic stainless steels. It combines good corrosion resistance and heat and oxidation with good mechanical properties. Typical product applications include automotive trim and molding, dishwashers, range hoods, steam iron bases, and flatware and restaurant equipments. Information provided by Eagle Brass Company

Order this product through the following link: http://www.lookpolymers.com/polymer_Eagle-Brass-430-Ferritic-Stainless-Steel-Full-Hardened.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|--------------------------|-------------|
| Density | 7.70 g/cc | 0.278 lb/in ³ | As Annealed |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|------------|---------------|-------------|
| Tensile Strength | >= 738 MPa | >= 107000 psi | |
| Tensile Strength, Yield | >= 689 MPa | >= 100000 psi | 0.2% Offset |
| Elongation at Break | >= 1.0 % | >= 1.0 % | in 2 inches |
| Tensile Modulus | 200 GPa | 29000 ksi | |

| Thermal Properties | Metric | English | Comments |
|----------------------|-------------------------------|-----------------------------------|----------|
| CTE, linear | 11.9 µm/m-°C | 6.60 µin/in-°F | |
| | @Temperature 20.0 - 649 °C | @Temperature 68.0 - 1200 °F | |
| Thermal Conductivity | 26.1 W/m-K | 181 BTU-in/hr-ft ² -°F | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------------|--------------|-----------------------|
| Carbon, C | <= 0.12 % | <= 0.12 % | |
| Chromium, Cr | 16 - 18 % | 16 - 18 % | |
| Iron, Fe | 79.81 - 84 % | 79.81 - 84 % | Calculated as Balance |
| Manganese, Mn | <= 1.0 % | <= 1.0 % | |
| Phosphorous, P | <= 0.040 % | <= 0.040 % | |
| Silicon, Si | <= 1.0 % | <= 1.0 % | |
| Sulfur, S | <= 0.030 % | <= 0.030 % | |



Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China