

Eagle Brass 521 Phosphor Bronzes 8% C, 3/4 Hard

Category : Metal , Nonferrous Metal , Copper Alloy , Bronze

Material Notes:

Alloy C521 is a high tin alloy of the phosphor bronze family. The additional tin relative to the more commonly used C510 results in higher mechanical properties with a modest reduction in electrical conductivity. Applications include electronic parts, springs, contacts, switch parts and fasteners. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-521-Phosphor-Bronzes-8-C-34-Hard.php

Physical Properties	Metric	English	Comments
Density	8.80 g/cc	0.318 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	71 - 78	71 - 78	Thickness > 0.020 Inch
Tensile Strength, Ultimate	552 - 565 MPa	80000 - 82000 psi	
Tensile Strength, Yield	483 - 586 MPa	70000 - 85000 psi	0.2% offset
Elongation at Break	18 - 32 %	18 - 32 %	in 2 in.
Tensile Modulus	110 GPa	16000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.2 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.1 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	62.3 W/m-K	432 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	91.9 %	91.9 %	
Phosphorous, P	0.10 %	0.10 %	
Tin, Sn	8.0 %	8.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000137 ohm-cm	0.0000137 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China