

Eagle Brass 7026 Copper Nickel, Annealed

Category : Metal , Nonferrous Metal , Copper Alloy

Material Notes:

7026 is a high performance alloy used in springs, terminals, elevated temperature interconnects and high reliability telecommunication components. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-7026-Copper-Nickel-Annealed.php

Physical Properties	Metric	English	Comments
Density	8.86 g/cc	0.320 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	552 - 689 MPa	80000 - 100000 psi	
Tensile Strength, Yield	>= 448 MPa	>= 65000 psi	0.2% offset
Elongation at Break	>= 10 %	>= 10 %	in 2 in.
Tensile Modulus	131 GPa	19000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	10.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 20.0 - 300 $^{\circ}\text{C}$	@Temperature 68.0 - 572 $^{\circ}\text{F}$	
Thermal Conductivity	15.6 W/m-K	108 BTU-in/hr-ft ² - $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Copper, Cu	97 %	97 %	
Nickel, Ni	2.0 %	2.0 %	
Silicon, Si	0.40 %	0.40 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000445 ohm-cm	0.00000445 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China