

## Eagle Brass 70265 XP175, Hard

Category : Metal , Nonferrous Metal , Copper Alloy

**Material Notes:**

Information provided by Eagle Brass Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eagle-Brass-70265-XP175-Hard.php](http://www.lookpolymers.com/polymer_Eagle-Brass-70265-XP175-Hard.php)

Physical Properties	Metric	English	Comments
Density	8.86 g/cc	0.320 lb/in <sup>3</sup>	Annealed

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	758 - 862 MPa	110000 - 125000 psi	
Tensile Strength, Yield	>= 689 MPa	>= 100000 psi	0.2% offset
Elongation at Break	>= 1.0 %	>= 1.0 %	in 2 in.
Tensile Modulus	131 GPa	19000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	10.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 20.0 - 300 $^{\circ}\text{C}$	@Temperature 68.0 - 572 $^{\circ}\text{F}$	
Thermal Conductivity	15.6 W/m-K	108 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Copper, Cu	97 %	97 %	
Nickel, Ni	2.0 %	2.0 %	
Silicon, Si	0.40 %	0.40 %	
Tin, Sn	0.42 %	0.42 %	
Zinc, Zn	0.30 %	0.30 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000445 ohm-cm	0.00000445 ohm-cm	Annealed

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China