

Eagle Brass 725 Copper Nickel Tin, Spring

Category : Metal , Nonferrous Metal , Copper Alloy

Material Notes:

Alloy C725 is a moderate strength, low conductivity alloy with excellent bare solderability and corrosion resistance. Applications include electronic parts, springs, connectors and wire wrap terminals. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-725-Copper-Nickel-Tin-Spring.php

Physical Properties	Metric	English	Comments
Density	8.89 g/cc	0.321 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	76 - 80	76 - 80	Thickness > 0.020 Inch
Tensile Strength, Ultimate	586 - 689 MPa	85000 - 100000 psi	
Tensile Strength, Yield	572 - 669 MPa	83000 - 97000 psi	0.2% offset
Elongation at Break	1.0 - 2.0 %	1.0 - 2.0 %	in 2 in.
Tensile Modulus	138 GPa	20000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	16.6 µm/m-°C	9.20 µin/in-°F	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	53.6 W/m-K	372 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	88.2 %	88.2 %	
Nickel, Ni	9.5 %	9.5 %	
Tin, Sn	2.3 %	2.3 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000162 ohm-cm	0.0000162 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China