

## **Eagle Brass 762 Nickel Silver 12%, Extra Spring**

Category: Metal, Nonferrous Metal, Nickel Alloy

## **Material Notes:**

762 is a nickel silver alloy that has excellent strength, stress relaxation resistance, and solderability. Due to it being extremely resistant to corrosion it doesn't tarnish easily and has a long shelf life. Typical uses include springs for relays, condensers, and decorative belt buckles. Information provided by Eagle Brass Company

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Eagle-Brass-762-Nickel-Silver-12-Extra-Spring.php

| Physical Properties | Metric    | English                  | Comments |
|---------------------|-----------|--------------------------|----------|
| Density             | 8.58 g/cc | 0.310 lb/in <sup>3</sup> | Annealed |

| Mechanical Properties      | Metric     | English       | Comments               |
|----------------------------|------------|---------------|------------------------|
| Hardness, Rockwell 30T     | >= 81      | >= 81         | Thickness > 0.020 Inch |
| Tensile Strength, Ultimate | >= 786 MPa | >= 114000 psi |                        |
| Tensile Strength, Yield    | >= 703 MPa | >= 102000 psi | 0.2% offset            |
| Elongation at Break        | <= 1.0 %   | <= 1.0 %      | in 2 in.               |
| Tensile Modulus            | 124 GPa    | 18000 ksi     |                        |

| Thermal Properties   | Metric                     | English                           | Comments |
|----------------------|----------------------------|-----------------------------------|----------|
| CTE, linear          | 16.2 μm/m-°C               | 9.00 μin/in-°F                    |          |
|                      | @Temperature 20.0 - 300 °C | @Temperature 68.0 -<br>572 °F     |          |
| Thermal Conductivity | 41.5 W/m-K                 | 288 BTU-in/hr-ft <sup>2</sup> -°F |          |

| Component Elements Properties | Metric | English | Comments |  |
|-------------------------------|--------|---------|----------|--|
| Copper, Cu                    | 59 %   | 59 %    |          |  |
| Nickel, Ni                    | 12 %   | 12 %    |          |  |
| Zinc, Zn                      | 29 %   | 29 %    |          |  |

| Electrical Properties  | Metric           | English          | Comments |
|------------------------|------------------|------------------|----------|
| Electrical Resistivity | 0.0000198 ohm-cm | 0.0000198 ohm-cm | Annealed |

## **Contact Songhan Plastic Technology Co.,Ltd.**



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China