

Eagle Brass 770 Nickel Silver 18%, Extra Spring

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

770 has good cold forming properties, is tarnish resistant and has very good spring properties. 770 does not become subject to embrittlement at lower temperature and it has excellent corrosion resistance. Typical uses include springs, resistance wire and optical goods. Information provided by Eagle Brass Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eagle-Brass-770-Nickel-Silver-18-Extra-Spring.php

Physical Properties	Metric	English	Comments
Density	8.69 g/cc	0.314 lb/in ³	Annealed

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 30T	>= 81	>= 81	Thickness > 0.020 Inch
Tensile Strength, Ultimate	>= 800 MPa	>= 116000 psi	
Tensile Strength, Yield	>= 793 MPa	>= 115000 psi	0.2% offset
Elongation at Break	<= 1.0 %	<= 1.0 %	in 2 in.
Tensile Modulus	124 GPa	18000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	16.7 $\mu\text{m}/\text{m}\cdot\text{C}$	9.30 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Thermal Conductivity	29.4 W/m-K	204 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	55 %	55 %	
Nickel, Ni	18 %	18 %	
Zinc, Zn	27 %	27 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000324 ohm-cm	0.0000324 ohm-cm	Annealed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China