

Eastman 15041 PET (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

Material Notes:

Voridian polymer 15041 is a PET thermoplastic polyester.Applications/UsesCrystallized PET (CPET) trays

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-15041-PET-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Bulk Density	0.817 g/cc	0.0295 lb/in ³	Poured; ASTM D1895
	0.881 g/cc	0.0318 lb/in ³	Vibrated; ASTM D1895
Density	1.40 g/cc	0.0506 lb/in ³	Crystalline Density; ASTM D1505
Melt Density	1.20 g/cc	0.0434 lb/in ³	ASTM D1238
	@Temperature 285 °C	@Temperature 545 °F	
Particle Size	2500 µm	2500 µm	Pellet Size
Viscosity Measurement	0.85	0.85	Intrinsic; VGAS-A-AN-G-V-1

Thermal Properties	Metric	English	Comments
Heat of Fusion	63.0 J/g	27.1 BTU/lb	ASTM E793
Specific Heat Capacity	1.10 J/g-°C	0.263 BTU/lb-°F	ASTM E1269
	1.30 J/g-°C	0.311 BTU/lb-°F	ASTM E1269
	@Temperature 80.0 °C	@Temperature 176 °F	
	1.40 J/g-°C	0.335 BTU/lb-°F	ASTM E1269
	@Temperature 100 °C	@Temperature 212 °F	
1.90 J/g-°C	0.454 BTU/lb-°F	ASTM E1269	
@Temperature 200 °C	@Temperature 392 °F		
2.10 J/g-°C	0.502 BTU/lb-°F	ASTM E1269	
@Temperature 280 °C	@Temperature 536 °F		
Melting Point	250 °C	482 °F	Crystalline Peak Melting Point; ASTM D3418

Descriptive Properties	Value	Comments
Acetaldehyde	<3ppm	VKCA-A-AS-G-GC-0001
Fines, wt%, max	0.1	TEPO-A-AN-G-GA-4

Descriptive Properties	Value	Comments
------------------------	-------	----------

Pellet Shape

Cubical

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China