

Eastman 1550A Polyethylene (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Injection molding grade Unless otherwise noted, all tests are run at 23°C and 50% RH. Where required, samples are compression molded per ASTM D1928. Information from manufacturer data sheet. Eastman Chemical Company sold its polyethylene business to Westlake Chemical Corporation in Dec. 2006. This grade no longer appears in the Westlake product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-1550A-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ASTM D1505
Melt Flow	3.5 g/10 min @Load 2.16 kg, Temperature 190 °C	3.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	11.0 MPa	1600 psi	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Tensile Strength, Yield	12.0 MPa	1740 psi	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Elongation at Break	500 %	500 %	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Flexural Modulus	0.207 GPa	30.0 ksi	2% Secant, 12.7 mm/min. (0.5 in./min.); ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	89.0 °C	192 °F	ASTM D1525
Brittleness Temperature	<= -73.0 °C	<= -99.4 °F	ASTM D746

Descriptive Properties	Value	Comments
Process	Injection	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China