

## Eastman 808P Polyethylene (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

### Material Notes:

Low density polyethylene 808P is a low density resin designed for applications, such as sugar pouches and freezer wrap, where high coating speeds and good drawdown are required. The combination of high melt index and low density also provides good heat seals at high packaging or sealing rates. Unless otherwise noted, all tests are run at 23°C and 50% RH. Information from manufacturer data sheet. Eastman Chemical Company sold its polyethylene business to Westlake Chemical Corporation in Dec. 2006. This grade no longer appears in the Westlake product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eastman-808P-Polyethylene-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Eastman-808P-Polyethylene-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in <sup>3</sup>	ASTM D4883
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 °C	7.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	10.0 MPa	1450 psi	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Tensile Strength, Yield	10.0 MPa	1450 psi	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Elongation at Break	400 %	400 %	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Flexural Modulus	0.207 GPa	30.0 ksi	2% Secant, 12.7 mm/min. (0.5 in./min.); ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	88.0 °C	190 °F	ASTM D1525
Brittleness Temperature	<= -73.0 °C	<= -99.4 °F	ASTM D746

Descriptive Properties	Value	Comments
Process	Coating	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**