

Eastman Eastar GN005 Copolyester, Natural (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

Material Notes:

Eastar GN005 Copolyester is a glycol modified polyethylene terephthalate (PET) with an added mold release. Eastar GN005 copolyester will not crystallize and thus offers wider processing latitude than conventional crystallizable polyesters. This material offers an excellent combination of clarity, toughness, and melt strength that makes it useful for a variety of processing techniques and end-use applications. Applications/Uses Blister packaging

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-Eastar-GN005-Copolyester-Natural-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|-----------------------|-----------------------|---------------------------|--------------------------|
| Specific Gravity | 1.27 g/cc | 1.27 g/cc | ASTM D792 |
| Density | 1.27 g/cc | 0.0459 lb/in ³ | ISO 1183 |
| Water Absorption | 0.13 % | 0.13 % | 24h Immersion; ISO 62 |
| | 0.13 % | 0.13 % | 24h Immersion; ASTM D570 |
| Linear Mold Shrinkage | 0.0020 - 0.0050 cm/cm | 0.0020 - 0.0050 in/in | ASTM D955 |
| | @Thickness 3.20 mm | @Thickness 0.126 in | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|----------|-----------|-----------|
| Hardness, Rockwell R | 106 | 106 | ASTM D785 |
| Tensile Strength at Break | 28.0 MPa | 4060 psi | ISO 527 |
| | 28.0 MPa | 4060 psi | ASTM D638 |
| Tensile Strength, Yield | 50.0 MPa | 7250 psi | ASTM D638 |
| | 50.0 MPa | 7250 psi | ISO 527 |
| Elongation at Break | 60 % | 60 % | ISO 527 |
| | 110 % | 110 % | ASTM D638 |
| Elongation at Yield | 4.2 % | 4.2 % | ISO 527 |
| | 4.3 % | 4.3 % | ASTM D638 |
| Flexural Yield Strength | 68.0 MPa | 9860 psi | ISO 178 |
| | 70.0 MPa | 10200 psi | ASTM D790 |
| Flexural Modulus | 2.00 GPa | 290 ksi | ISO 178 |

| Mechanical Properties | 2.10 GPa ^a Metric | 305 ksi ^a English | ASTM D790 Comments |
|----------------------------|---------------------------------|---------------------------------|--|
| Izod Impact, Notched | 0.370 J/cm | 0.693 ft-lb/in | ASTM D256 |
| | @Temperature -40.0 °C | @Temperature -40.0 °F | |
| | 1.01 J/cm | 1.89 ft-lb/in | ASTM D256 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |
| Izod Impact, Unnotched | NB | NB | ASTM D4812 |
| | NB | NB | ASTM D4812 |
| | @Temperature -40.0 °C | @Temperature -40.0 °F | |
| Izod Impact, Notched (ISO) | 4.20 kJ/m ² | 2.00 ft-lb/in ² | ISO 180 |
| | @Temperature -40.0 °C | @Temperature -40.0 °F | |
| | 6.20 kJ/m ² | 2.95 ft-lb/in ² | ISO 180 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |
| Puncture Energy | 12.0 J | 8.85 ft-lb | Puncture Resistance @ max load, 23°C; ISO 6603-2 |
| | 13.0 J | 9.59 ft-lb | Puncture Resistance at Max Load; ISO 6603-2 |
| | @Temperature -40.0 °C | @Temperature -40.0 °F | |

| Thermal Properties | Metric | English | Comments |
|---|----------------------|------------------------------------|----------------------|
| Specific Heat Capacity | 1.30 J/g-°C | 0.311 BTU/lb-°F | DSC |
| | @Temperature 60.0 °C | @Temperature 140 °F | |
| | 2.01 J/g-°C | 0.480 BTU/lb-°F | DSC |
| | @Temperature 240 °C | @Temperature 464 °F | |
| Thermal Conductivity | 0.190 W/m-K | 1.32 BTU-in/hr-ft ² -°F | ASTM C177 |
| Deflection Temperature at 0.46 MPa (66 psi) | 70.0 °C | 158 °F | ISO 75 |
| | 70.0 °C | 158 °F | ASTM D648 |
| Deflection Temperature at 1.8 MPa (264 psi) | 64.0 °C | 147 °F | ISO 75 |
| | 64.0 °C | 147 °F | ASTM D648 |
| Vicat Softening Point | 76.0 °C | 169 °F | 5kg load; ISO 306 |
| | 85.0 °C | 185 °F | 1kg load; ISO 306 |
| | 85.0 °C | 185 °F | 1kg load; ASTM D1525 |

| Thermal Properties | ^{HB} Metric | ^{HB} English | Comments |
|--------------------|-------------------------|--------------------------|----------|
| | @Thickness 1.60 mm | @Thickness 0.0630 in | |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------------|---------------|----------|
| Melt Temperature | 250 - 270 °C | 482 - 518 °F | |
| Mold Temperature | 15.0 - 40.0 °C | 59.0 - 104 °F | |
| Drying Temperature | 70.0 °C | 158 °F | |
| Dry Time | 6 hour | 6 hour | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China