

Eastman Voridian D4009-A Polyethylene (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Voridian polyethylene D4009-A is a low density formulation used for injection molding. It is an outstanding material for molding lids and other container closures because it processes easily on automatic molding equipment to produce molded items with excellent gloss, clarity, and warpage resistance. Information supplied by the manufacturer. Information from manufacturer data sheet. Eastman Chemical Company sold its polyethylene business to Westlake Chemical Corporation in Dec. 2006. This grade no longer appears in the Westlake product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eastman-Voridian-D4009-A-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D4883
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 190 °C	20 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	8.00 MPa	1160 psi	500 mm/min (20 in./min.); Type IV Specimen; ASTM D638
Tensile Strength, Yield	11.0 MPa	1600 psi	500 mm/min (20 in./min.); Type IV Specimen; ASTM D638
Elongation at Break	90 %	90 %	500 mm/min (20 in./min.); Type IV Specimen; ASTM D638
Flexural Modulus	0.228 GPa	33.1 ksi	2% Secant, 12.7 mm/min. (0.5 in./min.); ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 °C	194 °F	ASTM D1525
Brittleness Temperature	-45.0 °C	-49.0 °F	ASTM D746

Descriptive Properties	Value	Comments
Process	Injection	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China