

**Eastman Voridian E6838-010A Polyethylene (discontinued \*\*)**

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

**Material Notes:**

Voridian polyethylene E6838-010A is a low density formulation with medium slip used for injection molding. It is an outstanding material for molding lids and other container closures because it processes easily on automated molding equipment to produce molded items with excellent gloss, clarity, and warpage resistance. Users must make their own determination that use of this product is safe, legal, and technically suitable for their intended applications. Information from manufacturer data sheet. Eastman Chemical Company sold its polyethylene business to Westlake Chemical Corporation in Dec. 2006. This grade no longer appears in the Westlake product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Eastman-Voridian-E6838-010A-Polyethylene-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Eastman-Voridian-E6838-010A-Polyethylene-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D 4883
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 190 °C	20 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	8.00 MPa	1160 psi	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Tensile Strength, Yield	11.0 MPa	1600 psi	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Elongation at Break	90 %	90 %	500 mm/min (20 in./min.); ASTM D638, Type IV Specimen
Flexural Modulus	0.228 GPa	33.1 ksi	2% Secant, 12.7 mm/min. (0.5 in./min.); ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 °C	194 °F	ASTM D1525
Brittleness Temperature	-45.0 °C	-49.0 °F	ASTM D746

Descriptive Properties	Value	Comments
Process	Injection	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China