

Ecomass® 1850ZD88 Tungsten Filled Polyamide

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Nontoxic alternative to Lead (Pb), weighting and balancing applications
High Specific Gravity
Tungsten Powder Filled Polyamide (PA6)
Information provided by Technical Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ecomass-1850ZD88-Tungsten-Filled-Polyamide.php

Physical Properties	Metric	English	Comments
Specific Gravity	6.50 g/cc	6.50 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	48.3 MPa	7000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Tensile Modulus	11.0 GPa	1600 ksi	ASTM D638
Flexural Strength	93.1 MPa	13500 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 °C	250 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	246 - 254 °C	475 - 490 °F	
Mold Temperature	57.2 - 82.2 °C	135 - 180 °F	
Drying Temperature	73.9 °C	165 °F	
Dry Time	4 hour	4 hour	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China