

## Elastocon TPE Technologies Elastocon® 2880L Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

**Material Notes:**

Elastocon® 2880L thermoplastic elastomer has been developed for applications that require rubber-like properties and a reduced coefficient of friction. Elastocon® 2880L is FDA compliant and well suited for consumer goods and industrial applications. Elastocon® 2880L can be overmolded onto polypropylene. Information provided by Elastocon® TPE Technologies

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Elastocon-TPE-Technologies-Elastocon-2880L-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Elastocon-TPE-Technologies-Elastocon-2880L-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.880 g/cc	0.880 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.014 - 0.024 cm/cm	0.014 - 0.024 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	ASTM D2240
Tensile Strength, Yield	8.246 MPa	1196 psi	ASTM D412
Elongation at Break	526 %	526 %	ASTM D412
100% Modulus	0.00445 GPa	0.646 ksi	ASTM D412
Compression Set	18 % @Time 79200 sec	18 % @Time 22.0 hour	ASTM D395B

Processing Properties	Metric	English	Comments
Feed Temperature	79.0 °C	174 °F	
Rear Barrel Temperature	166 - 177 °C	330 - 350 °F	
Front Barrel Temperature	182 - 188 °C	360 - 370 °F	
Nozzle Temperature	193 - 204 °C	380 - 400 °F	
Mold Temperature	21.1 - 37.8 °C	70.0 - 100 °F	
Back Pressure	0.689 - 1.38 MPa	100 - 200 psi	

Descriptive Properties	Value	Comments
Injection Rate	Fast	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China