

Elastocon TPE Technologies Elastocon® SMR1600 Thermoplastic Polyolefin Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO)

Material Notes:

Elastocon® SMR1600 thermoplastic polyolefin elastomer has been developed for applications that require low temperature impact resistance and a high gloss scratch and mar resistant surface finish. Elastocon® SMR1600 is well suited for consumer goods and industrial applications requiring U.V. stability and excellent low temperature stability. Elastocon® SMR1600 provides a non-bloom surface. Information provided by Elastocon® TPE Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elastocon-TPE-Technologies-Elastocon-SMR1600-Thermoplastic-Polyolefin-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.890 g/cc	0.890 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.015 - 0.025 cm/cm	0.015 - 0.025 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	ASTM D2240
Tensile Strength, Yield	20.2 MPa	2930 psi	ASTM D412
Elongation at Break	542 %	542 %	ASTM D412
100% Modulus	0.0160 GPa	2.32 ksi	ASTM D412
Dynatup @ -30°C	39.2 J	28.9 ft-lb	ASTM D3763

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	200 - 225 °C	392 - 437 °F	
Front Barrel Temperature	200 - 230 °C	392 - 446 °F	
Nozzle Temperature	200 - 235 °C	392 - 455 °F	
Mold Temperature	21.0 - 49.0 °C	69.8 - 120 °F	
Back Pressure	0.689 - 1.38 MPa	99.9 - 200 psi	

Descriptive Properties	Value	Comments
Injection Velocity (mm/sec)	Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China