

Elgiloy® Co-Cr-Ni Alloy, Wire, 10% Cold Reduction

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

Material Notes:

The strength, shear modulus, and hardness values are specific to this cold reduction treatment; other values below are typical of Elgiloy®. General Elgiloy® information: High strength, ductility, fatigue life, and good mechanical properties. Corrosion resistant in numerous environments. Available in strip (currently 0.0015" to 0.075" thickness and 0.023" to 9.00 " width), round wire (0.006" to 0.625" diameter), sheet, cable, ribbon, bar, rod, and some fabricated parts. General Forming Notes: Forming should be done prior to heat treatment since heat treatment strengthens the material and makes it more difficult to form. Bending of strip should take place perpendicular to the rolling direction so that it will be across the elongated grain structure rather than parallel to it. In bending strip, a 90° bend should be at least 8 times the material thickness; in a 360° bend, a diameter of 18 to 25 times the material thickness is usually acceptable. Wire should not be formed beyond a mean diameter of 4 times the wire size.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elgiloy-Co-Cr-Ni-Alloy-Wire-10-Cold-Reduction.php

Physical Properties	Metric	English	Comments
Density	8.30 g/cc	0.300 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	259	259	Estimated from Rockwell C
Hardness, Knoop	306	306	Estimated from Rockwell C
Hardness, Rockwell A	63	63	Estimated from Rockwell C
Hardness, Rockwell B	102	102	Estimated from Rockwell C; beyond normal Rockwell B range.
Hardness, Rockwell C	26	26	
Hardness, Vickers	267	267	Estimated from Rockwell C
Tensile Strength, Ultimate	1070 MPa	155000 psi	
Tensile Strength, Yield	690 MPa	100000 psi	
Modulus of Elasticity	186 GPa	27000 ksi	Calculated
Poissons Ratio	0.226	0.226	
Shear Modulus	76.0 GPa	11000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	15.17 µm/m-°C	8.428 µin/in-°F	
	@Temperature 0.000 -	@Temperature 32.0 -	

Thermal Properties	500 °C Metric	932 °F English	Comments
Specific Heat Capacity	0.430 J/g-°C	0.103 BTU/lb-°F	
Thermal Conductivity	12.5 W/m-K	86.8 BTU-in/hr-ft²-°F	
Melting Point	1427 °C	2601 °F	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	<= 0.10 %	<= 0.10 %	
Carbon, C	<= 0.15 %	<= 0.15 %	
Chromium, Cr	19 - 21 %	19 - 21 %	
Cobalt, Co	39 - 41 %	39 - 41 %	
Iron, Fe	11.25 - 20.5 %	11.25 - 20.5 %	As remainder
Manganese, Mn	1.5 - 2.5 %	1.5 - 2.5 %	
Molybdenum, Mo	6.0 - 8.0 %	6.0 - 8.0 %	
Nickel, Ni	14 - 16 %	14 - 16 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000996 ohm-cm	0.0000996 ohm-cm	
Magnetic Permeability	1.0004	1.0004	For all practical purposes, Elgiloy® is nonmagnetic through all temperature ranges.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China