

## Elgiloy® Co-Cr-Ni Alloy, Wire, 20% Cold Reduction

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

### Material Notes:

The strength, shear modulus, and hardness values are specific to this cold reduction treatment; other values below are typical of Elgiloy®. General Elgiloy® information: High strength, ductility, fatigue life, and good mechanical properties. Corrosion resistant in numerous environments. Available in strip (currently 0.0015" to 0.075" thickness and 0.023" to 9.00 " width), round wire (0.006" to 0.625" diameter), sheet, cable, ribbon, bar, rod, and some fabricated parts. General Forming Notes: Forming should be done prior to heat treatment since heat treatment strengthens the material and makes it more difficult to form. Bending of strip should take place perpendicular to the rolling direction so that it will be across the elongated grain structure rather than parallel to it. In bending strip, a 90° bend should be at least 8 times the material thickness; in a 360° bend, a diameter of 18 to 25 times the material thickness is usually acceptable. Wire should not be formed beyond a mean diameter of 4 times the wire size.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Elgiloy-Co-Cr-Ni-Alloy-Wire-20-Cold-Reduction.php](http://www.lookpolymers.com/polymer_Elgiloy-Co-Cr-Ni-Alloy-Wire-20-Cold-Reduction.php)

Physical Properties	Metric	English	Comments
Density	8.30 g/cc	0.300 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	305	305	Estimated from Rockwell C
Hardness, Knoop	363	363	Estimated from Rockwell C
Hardness, Rockwell A	67	67	Estimated from Rockwell C
Hardness, Rockwell C	33	33	
Hardness, Vickers	317	317	Estimated from Rockwell C
Tensile Strength, Ultimate	1210 MPa	175000 psi	
Tensile Strength, Yield	880 MPa	128000 psi	
Modulus of Elasticity	184 GPa	26700 ksi	Calculated
Poissons Ratio	0.226	0.226	
Shear Modulus	75.0 GPa	10900 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	15.17 µm/m-°C	8.428 µin/in-°F	
	@Temperature 0.000 - 500 °C	@Temperature 32.0 - 932 °F	
Specific Heat Capacity	0.430 J/g-°C	0.103 BTU/lb-°F	

Thermal Properties	Metric	English	Comments
Melting Point	1427 °C	2601 °F	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	<= 0.10 %	<= 0.10 %	
Carbon, C	<= 0.15 %	<= 0.15 %	
Chromium, Cr	19 - 21 %	19 - 21 %	
Cobalt, Co	39 - 41 %	39 - 41 %	
Iron, Fe	11.25 - 20.5 %	11.25 - 20.5 %	As remainder
Manganese, Mn	1.5 - 2.5 %	1.5 - 2.5 %	
Molybdenum, Mo	6.0 - 8.0 %	6.0 - 8.0 %	
Nickel, Ni	14 - 16 %	14 - 16 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000996 ohm-cm	0.0000996 ohm-cm	
Magnetic Permeability	1.0004	1.0004	For all practical purposes, Elgiloy® is nonmagnetic through all temperature ranges.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China