

Elisto THERMOSTAR® MD 100 Pattern material

Category : Other Engineering Material

Material Notes:

Densified laminated wood Information provided by elisto

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elisto-THERMOSTAR-MD-100-Pattern-material.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 g/cc	1.00 g/cc	
Water Absorption	>= 5.0 %	>= 5.0 %	

Mechanical Properties	Metric	English	Comments
Flexural Strength	90.0 MPa	13100 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Modulus	8.00 GPa	1160 ksi	
Compressive Strength	140 MPa	20300 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Descriptive Properties	Value	Comments
Application Temperature (°C)	110	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China