

Elisto THERMOSTAR® XPS Mold Insulation Material

Category : Other Engineering Material

Material Notes:

Lateral insulation Information provided by elisto

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elisto-THERMOSTAR-XPS-Mold-Insulation-Material.php

Mechanical Properties	Metric	English	Comments
Flexural Strength	200 MPa	29000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Strength	3.00 MPa	435 psi	
	@Temperature 200 °C	@Temperature 392 °F	
	5.00 MPa	725 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0700 W/m-K	0.486 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	210 °C	410 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China