

Category : Polymer , Thermoset , Epoxy

SONGHAN

Plastic Technology Co., Ltd.

Material Notes:

SF-32 is a specially engineered syntactic formulated to serve as a void filler for subsea applications. The material is provided as a threepart kit that is mixed and poured into any free-flood cavity or void. The mix is allowed to cure at room temperature to form a solid syntactic material that will withstand repeated ocean excursions to depths of 3,000 feet. The easily cast system is provided in three parts; two resin components and a solid filler. The two resin components are mixed together, followed by the glass bubble filler. When the three materials are uniformly mixed, the moderate viscosity combination may be poured into its desired location. Initial cure will occur over a twenty four hour period at ambient temperatures, (50°F - 90 °F), providing a solid, lightweight article which is ready for any secondary operation such as machining, finishing or painting. Full cure will take place after 7 – 10 days. The cured material will provide an average of 32 pounds of buoyancy per cubic foot in seawater.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Engineered-Syntactic-Systems-SF-32-Subsea-Syntactic-Void-Filler.php

Physical Properties	Metric	English	Comments
Density	<= 0.513 g/cc	<= 0.0185 lb/in³	
Water Absorption	<= 3.0 %	<= 3.0 %	at 3000 ft.depth
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Compressive Strength	>= 16.5 MPa	>= 2400 psi	
Compressive Modulus	>= 1.10 GPa	>= 160 ksi	
Hydrostatic Design Basis	20.0 MPa	2900 psi	Hydrostatic Crush Strength (6600 feet)

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	from manufacture date
Descriptive Properties		Value	Comments
Color		White/Tan	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058



Skype : lookpolymers Address : United North Road 215, Fengxian District, Shanghai City, China