

Ensinger Sintimid™ V-HPHT high purity high temp Polyimide (PI) (discontinued **)

Category : Polymer , Thermoplastic , Polyimide, Thermoplastic

Material Notes:

SINTIMID™ V polyimide stock shapes provide a superior combination of high temperature and bearing and wear, properties that make it an idea choice for the most demanding applications. SINTIMID™ V is characterized by its long-term thermal stability, outstanding wear resistance, high creep resistance, and strength up to its continuous use temperature of 572°F. Specialty grades containing internal lubricants such as PTFE and graphite are available for applications requiring improved wear resistance and lower coefficients of friction. Superior high temperature characteristics Excellent long-term thermal stability Outstanding bearing and wear properties (at elevated temperatures, SINTIMID™ V formulations offer superior wear rates) Excellent creep resistance High strength and stiffness properties (SINTIMID™ V has a tensile strength of 20,000 psi at room temperature) High purity characteristics (only extremely low levels of extractables and ionic impurities are apparent in SINTIMID™ V) Good chemical resistance (SINTIMID™ V is not attacked by common solvents or fuels and is acceptable for use in contact with many acids) SINTIMID™ V with its superior physical properties, is ideal for applications in the aerospace, nuclear, automotive, electrical/electronic, and chemical processing industries. It is an excellent candidate for high purity applications in the semiconductor processing industry. Typical components produced from SINTIMID™ V include seals, thrust washers, bushings and wear pads in transportation/off-highway equipment, insulating and support elements in electrical welding and brazing equipment, and wafer-handling components in the harsh environment of semiconductor plasma ovens. Pump and valve seals, vanes, and piston rings are also commonly produced from SINTIMID™ V. Information Provided by Ensinger Industries, Inc. Sintimid has been replaced with Tecasint in the Ensinger product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-Sintimid-V-HPHT-high-purity-high-temp-Polyimide-PI-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Density	1.35 g/cc	0.0488 lb/in ³	ASTM D792
Water Absorption	1.86 % @Temperature 22.8 °C, Time 86400 sec	1.86 % @Temperature 73.0 °F, Time 24.0 hour	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	125	125	ASTM D785
Tensile Strength, Yield	116 MPa @Temperature 22.8 °C	16800 psi @Temperature 73.0 °F	ASTM D638
Elongation at Break	9.0 % @Temperature 22.8 °C	9.0 % @Temperature 73.0 °F	ASTM D638
	174 MPa	25200 psi	

Flexural Strength Mechanical Properties	Metric @ Temperature 22.8 °C	English @ Temperature 73.0 °F	ASTM D790 Comments
Flexural Modulus	4.00 GPa @ Temperature 22.8 °C	580 ksi @ Temperature 73.0 °F	ASTM D790
Izod Impact, Notched	0.438 J/cm @ Temperature 22.8 °C	0.820 ft-lb/in @ Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	48.6 µm/m-°C	27.0 µin/in-°F	ASTM D696
Maximum Service Temperature, Air	280 °C	536 °F	Long Term
	330 °C	626 °F	Intermittent
Deflection Temperature at 1.8 MPa (264 psi)	368 °C	695 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+18 ohm-cm	1.00e+18 ohm-cm	ASTM D257
Dielectric Strength	19.7 kV/mm	500 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China