

Ensinger TECAPRO™ SAN Polypropylene (PP)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

TECAFORM™ (Polyacetal) and TECAPRO™ SAN (Polypropylene), provide an additional safety factor in reducing incidence of bacterial contamination. The raw materials are charged with an antimicrobial additive. These silver ions are released gradually to reduce the formation of bacterial. Less bacterial contamination Reduced odor and biofilm formation Diminished formation of bacteria in equipment Active components are harmless to humans Scrubbing surface renews antimicrobial effect FDA conformity of raw material, color pigments and antimicrobial additive TECAFORM™ SAN and TECAPRO™ SAN are ideal where continual sanitary and anti bacterial conditions are a requirement. Excellent for components in food processing equipments, bottling and canning machines, water handling and filtration equipment. Door handels and buttons in public places would benefit from reduction in transfer of bacteria. TECAPRO™ SAN is especially effective in surgical instruments, trays, work surfaces and cutting boards in medical as well as food storage and preparation areas. Information Provided by Ensinger Industries, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-TECAPRO-SAN-Polypropylene-PP.php

Physical Properties	Metric	English	Comments
Density	0.919 g/cc	0.0332 lb/in³	ASTM D792
Moisture Absorption at Equilibrium	0.050 % @Temperature 22.8 °C	0.050 % @Temperature 73.0 °F	equilibrium, 50% RH; ISO 62

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	100 MPa	14500 psi	ISO 2039/1,2
Tensile Strength, Yield	32.99 MPa	4785 psi	ASTM D638, DIN EN ISO 527
Elongation at Break	>= 30 %	>= 30 %	ASTM D638, ISO 527
Flexural Modulus	1.86 GPa	270 ksi	ASTM D790, ISO 178
Izod Impact Resistance	0.0689 J/cm²	0.328 ft-lb/in²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	163 °C	325 °F	DIN 53 736
Maximum Service Temperature, Air	100 °C	212 °F	Long Term
	121 °C	250 °F	Sort Term
Deflection Temperature at 1.8 MPa (264 psi)	86.1 °C	187 °F	ISO - 75/A
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China