

Ensinger Tecapeek® XP-103 Compression Molded PEEK Compound, 15% Carbon Fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Ensinger Special Polymers offers over twenty different VICTREX® PEEK blends to choose from and has the capability to blend custom compounds for specific applications. Compression molding results in lower amounts of scrap, uniform physical properties and fewer molded-in stresses. TECAPEEK is a high-performance engineering thermoplastic. This semi-crystalline material has a balance of high temperature mechanical properties, chemical and steam resistance, superior wear properties and processability which makes it unique. Applications Include: Bearings and Bushings Down-hole instrumentation Wear Rings Ball Valve Seats Electrical Components Back-up and V-Rings Piston Rings and Rider Bands Information provided by Ensinger Special Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-Tecapeek-XP-103-Compression-Molded-PEEK-Compound-15-Carbon-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in ³	ASTM D792
Filler Content	15 %	15 %	
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	104	104	ASTM D785
Hardness, Shore D	88	88	ASTM D2240
Tensile Strength	106 MPa	15400 psi	ASTM D638
Elongation at Break	2.8 %	2.8 %	ASTM D638
	3.3 %	3.3 %	Flexural Strain; ASTM D790
Tensile Modulus	7.58 GPa	1100 ksi	ASTM D638
Flexural Strength	203 MPa	29500 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Compressive Strength	167 MPa	24200 psi	ASTM D695
Compressive Modulus	3.45 GPa	500 ksi	ASTM D695
Izod Impact, Notched	0.342 J/cm	0.640 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric $^{\circ}\text{C}$	English $^{\circ}\text{F}$	Comments
Melting Point	343 $^{\circ}\text{C}$	649 $^{\circ}\text{F}$	DSC
Heat Distortion Temperature	253 $^{\circ}\text{C}$	487 $^{\circ}\text{F}$	ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	≤ 10000 ohm	≤ 10000 ohm	ASTM D257

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China