

## Ensinger Tecapeek® XP-90 Compression Molded PEEK Compound, 25% Fiberglass

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Glass Fiber Filled

### Material Notes:

Ensinger Special Polymers offers over twenty different VICTREX® PEEK blends to choose from and has the capability to blend custom compounds for specific applications. Compression molding results in lower amounts of scrap, uniform physical properties and fewer molded-in stresses. TECAPEEK is a high-performance engineering thermoplastic. This semi-crystalline material has a balance of high temperature mechanical properties, chemical and steam resistance, superior wear properties and processability which makes it unique. Typical Applications: Bearings and Bushings Down-hole instrumentation Wear Rings Ball Valve Seats Electrical Components Back-up and V-Rings Piston Rings and Rider Bands Information provided by Ensinger Special Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ensinger-Tecapeek-XP-90-Compression-Molded-PEEK-Compound-25-Fiberglass.php](http://www.lookpolymers.com/polymer_Ensinger-Tecapeek-XP-90-Compression-Molded-PEEK-Compound-25-Fiberglass.php)

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in <sup>3</sup>	ASTM D792
Filler Content	25 %	25 %	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	105	105	ASTM D785
Tensile Strength	104 MPa	15100 psi	ASTM D638
Elongation at Break	2.8 %	2.8 %	ASTM D638
Flexural Strength	148 MPa	21500 psi	ASTM D790
Flexural Modulus	5.86 GPa	850 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	343 °C	649 °F	DSC

Descriptive Properties	Value	Comments
Color	Tan	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China