

Ensinger Tecatron® XP-64B Compression Molded PPS Compound, 40% Fiberglass, Black Pigmented

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 40% Glass Fiber Filler

Material Notes:

Ensinger Special Polymers has over twenty different grades of TECATRON PPS available. Custom formulations can be blended to suit specific applications. Compression molding is amenable to short run production and yields products which are homogenous with low process stress. TECATRON PPS is a highly crystalline high-temperature thermoplastic with an excellent balance of cost, temperature resistance, strength, chemical resistance and flame retardance. TECATRON PPS is often used when long-term high-temperature performance and dimensional stability are a must, even in the presence of aggressive chemicals. Applications: Fuel

Injectors Manifolds Pumps Pistons Gears V-Packing Gaskets Bearings Information provided by Ensinger Special Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-Tecatron-XP-64B-Compression-Molded-PPS-Compound-40-Fiberglass-Black-Pigmented.php

Physical Properties	Metric	English	Comments
Density	1.72 g/cc	0.0621 lb/in ³	ASTM D792
Filler Content	40 %	40 %	
Water Absorption	0.030 % @Time 86400 sec	0.030 % @Time 24.0 hour	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	88	88	ASTM D2240
Tensile Strength	51.0 MPa	7400 psi	ASTM D638
Elongation at Break	1.0 %	1.0 %	ASTM D638
	1.5 %	1.5 %	Flexural Strain; ASTM D790
Tensile Modulus	8.27 GPa	1200 ksi	ASTM D638
Flexural Strength	86.2 MPa	12500 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Compressive Strength	172 MPa	25000 psi	ASTM D695
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	284 °C	543 °F	DSC

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.91e+15 ohm-cm	2.91e+15 ohm-cm	ASTM D257
Dielectric Constant	4.58 @Frequency 1.00e+6 Hz	4.58 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	9.17 kV/mm	233 kV/in	ASTM D149

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China