

Ensinger Tecatron® XP-66 Compression Molded PPS Compound, 30% Fiberglass

Category: Polymer, Thermoplastic, Polyphenylene Sulfide (PPS), Polyphenylene Sulfide (PPS) with 30% Glass Fiber Filler

Material Notes:

Ensinger Special Polymers has over twenty different grades of TECATRON PPS available. Custom formulations can be blended to suit specific applications. Compression molding is amenable to short run production and yields products which are homogenous with low process stress. TECATRON PPS is a highly crystalline high-temperature thermoplastic with an excellent balance of cost, temperature resistance, strength, chemical resistance and flame retardance. TECATRON PPS is often used when long-term high-temperature performance and dimensional stability are a must, even in the presence of aggressive chemicals. Applications: Fuel InjectorsManifoldsPumpsPistonsGearsV-Packing GasketsBearingsInformation provided by Ensinger Special Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ensinger-Tecatron-XP-66-Compression-Molded-PPS-Compound-30-Fiberglass.php

Physical Properties	Metric	English	Comments
Density	1.65 g/cc	0.0596 lb/in ³	ASTM D792
Filler Content	30 %	30 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	86	86	ASTM D2240
Tensile Strength	36.5 MPa	5300 psi	ASTM D638
Elongation at Break	1.1 %	1.1 %	ASTM D638
Tensile Modulus	6.89 GPa	1000 ksi	ASTM D638
Flexural Strength	64.8 MPa	9400 psi	ASTM D790
Flexural Modulus	5.86 GPa	850 ksi	ASTM D790

Descriptive Properties	Value	Comments
Color	Dark Brown	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China