

## Entec Hylex® P1010L1 HB Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

### Material Notes:

Available in North America Agency Ratings: FDA 21 CFR 177.1580 RoHS Compliant Form: Pellets Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hylex-P1010L1-HB-Polycarbonate.php](http://www.lookpolymers.com/polymer_Entec-Hylex-P1010L1-HB-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	72	72	ASTM D785
Tensile Strength at Break	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	130 %	130 %	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	138 °C	280 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542

Haze Optical Properties	1.0 % Metric	1.0 % English	ASTM D1003 Comments
Transmission, Visible	88 %	88 %	ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China