

Entec Hylex® P1010L2 HB Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Available in North America Additive: Mold Release Features: Good Mold Release and Medium Flow RoHS Compliant Form: Pellets

Appearance: Blue Information provided by Entec

Order this product through the following link:

http://www.lookpolymers.com/polymer_Entec-Hylex-P1010L2-HB-Polycarbonate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	72	72	ASTM D785
Tensile Strength at Break	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	130 %	130 %	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	139 °C	282 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	Unannealed; ASTM D648
Vicat Softening Point	154 °C	310 °F	ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542
Haze	1.0 % @Thickness 3.17 mm	1.0 % @Thickness 0.125 in	ASTM D1003
Transmission, Visible	88 % @Thickness 3.17 mm	88 % @Thickness 0.125 in	ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	ASTM D257
Dielectric Strength	15.0 kV/mm @Thickness 3.17 mm	380 kV/in @Thickness 0.125 in	In air; ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China