

## Entec Hypro™ PP-CP20/2 Impact Copolymer, 20 Melt Flow

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

This product is intended for general purpose injection molding applications including automotive and consumer products, large buckets and pails where toughness and cold temperature impact are required. Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hypro-PP-CP202-Impact-Copolymer-20-Melt-Flow.php](http://www.lookpolymers.com/polymer_Entec-Hypro-PP-CP202-Impact-Copolymer-20-Melt-Flow.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D1505
Linear Mold Shrinkage	0.014 cm/cm	0.014 in/in	ASTM D955
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 °C	20 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.0 MPa	3480 psi	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Flexural Modulus, 1% Secant	1160 MPa	168000 psi	ASTM D790
Izod Impact, Notched	>= 1.40 J/cm @Thickness 3.17 mm	>= 2.62 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China