

## Entec Hypro™ PP-HP12NS Homopolymer, 12 Melt Flow, Nucleated, Anti-stat, Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

Homopolymer, 12 Melt Flow, Nucleated, Anti-stat, Injection Molding Information provided by Entec

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Entec-Hypro-PP-HP12NS-Homopolymer-12-Melt-Flow-Nucleated-Anti-stat-Injection-Molding.php](http://www.lookpolymers.com/polymer_Entec-Hypro-PP-HP12NS-Homopolymer-12-Melt-Flow-Nucleated-Anti-stat-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D1505
Linear Mold Shrinkage	0.014 cm/cm	0.014 in/in	ASTM D955
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 230 °C	12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	38.0 MPa	5510 psi	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus, 1% Secant	1807 MPa	262100 psi	ASTM D790
Izod Impact, Notched	0.320 J/cm @Thickness 3.17 mm	0.599 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	116 °C	241 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China